



## Chemical constancy

	Polyamide	Polyester	Polypropylene	Wire cloth
Alkali	A/B	A/B	A	A
Acid	B/C	A/B	A	A
Alcohol	A	A	A	A
Ester	A	A	A	A
Aliphatic HC	A	A	A	A
Aromatic HC	A	B	C	A
Chloritic HC	A	A	B	A
Oxidant	B/C	B/C	A	A/B/C
Oils, Grease	B/C	A	A	A

### Temperature

dry	110°C	150°C	100°C	400°C
wet	100°C	120°C	90°C	400°C

### Legend

consistent = A

conditionally consistent = B

not consistent = C

The data are approximate values depending on the concentration of the suspension and the duration of the filtration process. For further information on individual chemicals, please contact us.